Concrete Semi Mountable Kerb A120.08



DESIGN STATEMENT

Concrete cast in situ semi mountable kerb allows movement of vehicles across the kerb line with a medium degree of discomfort.

APPLICABLE LOCATION

Semi mountable kerb should be used where occasional movements of vehicles across the kerb line are allowed such as edges of medians and approach splitter islands and where surface drainage is not required.

COUNCIL STANDARD DRAWING

SD 211 Semi-mountable kerb

CROSS REFERENCE DOCUMENT

 Australian Standard 1379 and Merri-bek Standard Specification Section 61 and 80.

STANDARD SPECIFICATION

Concrete semi mountable kerb should be cast in situ with premix concrete in accordance with Australian Standard 1379 and Merri-bek City Council Standard Specifications. **Concrete strength**: Concrete strength is to be 25 MPA (28 day compressive strength).

SUPPLIER

N/A

MAINTENANCE

Road Maintenance Unit: Replace damaged sections of kerb between joints. Do not repair small sections.

GENERAL NOTES

- 1. Concrete strength to be 25 MPa, unless specified otherwise.
- Charcoal coloured concrete, where specified, shall be by adding 'Abilox' black colour powder equivalent into the premix concrete. The rate of powder shall be 8.3% by weight of cementitious binder (approx. 25kg per cubic metre of concrete).



A120.08 Concrete Semi Mountable Kerb



